

Product Data



908 LENOIR ROAD • POST OFFICE BOX 1809
HICKORY, NORTH CAROLINA • 28603-1809
TELEPHONE (828) 328-1721
TOLL FREE (800) 334-5975
FAX (828) 328-4572

CC-4000 RED EPOXY PRIMER

CC-4000 is a two-component Red Oxide Primer specifically formulated for use on metal and plastic surfaces to enhance the adhesion and durability of subsequent topcoats.

CC-4000 must be blended with CC-1800 Epoxy Activator prior to use at a 1:1 ratio of CC-4000:CC-1800 and mixed thoroughly. We recommend that this mixture be allowed to set at least 30 minutes prior to application.

TYPICAL PROPERTIES OF CC-4000 EPOXY PRIMER

Color:	Red Oxide
Weight per Gallon:	11.75 Pounds
Viscosity, #2 Zahn Cup, 77°F	16-17 Seconds

APPLICATION AND FILM PROPERTIES

Mixing Ratio:	1 part by volume CC-4000 1 part by volume CC-1800
Dry to Touch Time	Approximately 15 minutes
Sanding Time:	2 - 4 hours
Pot Life of Mixed Material, 77°F:	Approximately 8 hours

page 1 of 1
HKR048-041190rev